

BEST AVAILABLE COPY

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 September 2001 (07.09.2001)

PCT

(10) International Publication Number
WO 01/64594 A1

(51) International Patent Classification⁷: C03C 3/04,
3/11, C03B 19/14, C01B 21/087, 21/082, C23C 16/30,
G02B 6/10

(21) International Application Number: PCT/IB00/01763

(22) International Filing Date:
28 November 2000 (28.11.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00810163.6 29 February 2000 (29.02.2000) EP

(71) Applicant (for all designated States except US): INTER-
NATIONAL BUSINESS MACHINES CORPORA-
TION [US/US]; New Orchard Road, Armonk, NY 10504
(US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BEYELER, René
[CH/CH]; Riedmuehlestrasse 21e, CH-8306 Bruettisellen
(CH). BLÖCHL, Peter [AT/CH]; Buechelring 13,

CH-8134 Adliswil (CH). BONA, Gian-Luca [CH/CH];
Lettenweidstrasse 10, CH-8908 Hedingen (CH). GER-
MANN, Roland, W. [DE/CH]; Donnerweidstrasse 18,
CH-8855 Wangen (CH). HORST, Folkert [NL/CH];
Hornhaldenstrasse 1, CH-8802 Kilchberg (CH). OF-
FREIN, Bert, J. [NL/CH]; Fuhrstrasse 19, CH-8135
Langnau (CH). SALEMINK, Huub, L. [NL/CH];
Saentisstrasse 75, CH-8820 Waendenswill (CH). WIES-
MANN, Dorothea, W. [DE/CH]; Staubstrasse 3, CH-8038
Zurich (CH).


(74) Agent: KLETT, Peter, Michael; International Busi-
ness Machines Corporation, Saeumerstrasse 4, CH-8803
Rueschlikon (CH).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,
DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,
RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian

[Continued on next page]

(54) Title: MATERIAL FOR SiON-OPTICAL WAVEGUIDES AND METHOD FOR FABRICATING SUCH WAVEGUIDES



(57) Abstract: A new material is provided that can be used for the fabrication of planar optical waveguides. The material includes silicon, oxygen and nitrogen and additionally deuterium. Also provided is a method for fabricating planar optical waveguides based on this new material, which uses deuterated gaseous precursors.

WO 01/64594 A1



patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*

D E S C R I P T I O N

Material for SiON-Optical Waveguides and Method for
5 Fabricating such Waveguides

Field of the Invention

10 The present invention relates to a material which can be used in the fabrication of optical waveguides. More specifically, the invention deals with such a material that includes silicon, oxygen and nitrogen. Still more specifically, the present invention pertains to a method for fabricating
15 waveguides including such material.

Background of the Invention, Prior Art

20 High-bandwidth communication today relies increasingly on optical fibers and optical components for signal enhancement, signal-routing, adding and dropping information. The requirement for high capacity communication systems has led to the use of optical waveguides. An optical waveguide consists
25 of a core made of some high-refractive index material and a cladding of a low- refractive-index material surrounding the core. In traditional optical-waveguide technology, the core and cladding are made of doped silica glass, where the refractive index contrast, i.e., the difference of the
30 refractive index of the core layer relative to the cladding layers, is achieved by a doping profile, e.g., using P-doping or Ge-doping. In order to fabricate optical components in a cost-effective way in mass production, it is desirable to increase the areal density. This can be achieved with the SiON
35 technology. A review on planar waveguide technology is given,

e.g., in „Silica-based optical integrated circuits“ by Y.P. Li and C.H. Henry; IEEE Proc.- Optoelectron., Vol. 143, No. 5, October 1996, pp. 263-280.

5 In order to increase the areal density compared to traditional technology, smaller bending radii are required. Smaller bending radii, however, require a stronger guiding of the optical modes than in a straight waveguide or fiber. This is achieved by increasing the refractive index contrast between
10 core and cladding. An example for a method for increasing the index of refraction of a glassy material is given in US-A-5,500,031, wherein the material is treated with hydrogen under the application of heat. However, the maximum doping levels with P, B, Ge or other dopants in SiO₂ (silica) limit the
15 maximum achievable index contrast and hence a minimal attainable bending radius in the waveguide exists. In both conventional fiber and planar Ge-silica (SiO₂) there is an index contrast ranging from 0.002 up to 0.006. This allows a
~~curvature radius of typically 15 mm. The index contrast in~~
20 SiON technology is typically 0.02 (i.e., 3x to 10x higher) and allows for a curvature radius down to 1.5 mm. This corresponds to an increase in areal density of 100x. A good compromise between the minimum bending radius and coupling losses to the standard fiber and the necessary difference in the material
25 composition between core and cladding resulting therefrom can be obtained, e.g., with an effective refractive-index contrast around 0.02.

If the cladding is made of silica, i.e., SiO₂, which has a
30 refractive index of 1.45, a material having a refractive index near 1.51 is desired for the core. Waveguides with such a high index contrast can be fabricated with silicon-oxinitride (SiON) core layers. An example for the use of SiON as a material for fabricating waveguides is given in
35 US-A-5,416,861.

Owing to the nitrogen „doped“ silicon-oxide compound, the refractive index can be adjusted in a very flexible way to match other design criteria such as, e.g., achievable dimensions. A relatively high effective lateral contrast in refractive index can be used which is approximately 10 x higher than that used for Ge-doped SiO_2 waveguides. This allows a 10 x smaller radius of curvature (1.5 mm) to be used in circuit layouts.

10

A typical fabrication technique is to deposit silicon oxinitride by means of a PECVD process using silane (SiH_4), nitrous-oxide (N_2O), and ammonia (NH_3) as gaseous precursors. The resulting material, however, has a large hydrogen concentration. Hydrogen is incorporated in the form of hydroxyl groups, Si-H groups and NH- and NH_2 -fragments. These groups and fragments introduce additional absorption into the optical transmission characteristic of the silicon oxinitride. The first overtone of the NH-induced absorption lies at 1510 nm and overlaps with the spectral window which is used for optical signal transmission and which extends from 1540 nm to 1570 nm, hereinafter simply referred to as the optical transmission window. This window has been chosen for optical transmission due to the fact that the optical transmission losses are minimal around 1550 nm (due to purity of fabrication) and that for all-optical amplifiers in fiber networks (avoiding electrical-optical conversions) the only currently available amplifiers are based on Er (Erbium)-doping of SiO_2 fibers and the resultant amplification window is limited to 1540-1570 nm. Therefore, the accepted standard for the optical telecommunication frequencies has been assigned to this window (cf. „Review of Rare Earth Doped Fiber Lasers and Amplifiers“ by P. Urquhart; IEEE Proc., Vol. 135, Pt. J, No. 6, December 1988, pp. 385-407.

35

The above mentioned NH-absorption results in often unacceptably large losses for viable products. The hydrogen concentration and with it the resulting absorption losses are therefore currently reduced by a high-temperature annealing process as described, e.g., in MRS Proceedings Book of the 1999 Spring Meeting of the MRS Materials Research Society, „Materials Research Society (MRS) Spring Meeting 1999, 5-8 April 1999, Paper BB.8.3, Symposium BB on Multicomponent Oxides“, MRS Proceedings Volume 574, pp. 255-260, 1999 (ISBN 1-55899-481-5). The process consolidates the SiON material, and removes hydrogen from the N-H bond in the form of H₂ and H₂O. In conventional SiON material (SiON:H), the losses are reduced to lower values by higher anneal temperatures or longer anneal durations, but both routes bear the risk of introducing unwanted defect-scattering or crystallization. A further negative side effect of the high-temperature annealing is the introduction of anisotropic stress, caused by the difference in thermal expansion coefficients between the silicon-substrate and the material of the waveguide. The stress correlates with the temperature difference between room temperature and the highest annealing temperature or a material-specific temperature close to its annealing point, whichever is lower. The stress gives rise to birefringence and polarization-dependent transmission characteristics and is not desired for most applications.

It is known in the art of fiber manufacturing to use deuterium in place of hydrogen to produce glass having a low hydroxyl group (-OH) content. The hydroxyl group normally present in glass produced in the presence of hydrogen is replaced by the deuterium containing ion OD⁻. Absorption peaks normally caused by the presence of the hydroxyl ions are shifted to longer wavelengths at which the absorptions are not troublesome when the waveguide is used to transmit light in the band of approximately 7,000 Å. Thus, US-A-3,791,714 discloses the

production of a SiO₂-waveguide by a flame hydrolysis process using deuterium gas or a deuterium compound gas which is passed through a liquid containing a silicon compound such as silicon tetrachloride. The resulting vapor is burned at high
5 temperatures (about 1800°C) to deposit a film of silicon dioxide on a rotating mandrel, resulting in a „soot“ deposit that contains OD-bonds instead of the usual OH-groups.

US-A-5,872,387 discloses semiconductor devices, including MOS
10 devices, that are treated with deuterium to improve their operational characteristics. The process comprises a step of passivating the device with deuterium by disposing molecular, atomic or ionic deuterium in the areas of the device in which protection against hot carrier effects is desired. The
15 deuterium is covalently bonded with atoms in this area so as to be stable incorporated.

A plate plastics optical waveguide is described in US-A-5,062,680 which includes a core portion composed of a polymer
20 containing a deuterium atom or a halogen atom, and a clad portion surrounding the core portion, the clad portion being composed of a polymer having a refractive index lower than that of the core portion.

25 While US-A-5,872,387 only describes a post-fabrication passivation in a heated, deuterium gas-enriched atmosphere, and US-A-5,062,680 uses a polymer containing deuterium to produce the optical waveguide, the main disadvantage of US-A-3,791,714 is the fact that the optical waveguide prepared
30 according to the process given therein still contains hydroxyl groups and is only applicable to manufacture waveguides in the form of fibers.

Accordingly, there is still a need for slab optical waveguides based on SiON material having extreme small optical losses and
35 very low mechanical stress.

Summary of the Invention

It is an object of the present invention to provide silicon-
5 oxinitride (SiON) layers for applications as planar optical
waveguides having extreme low optical losses in the region of
operation.

It is also an object of the present invention to provide a
10 low-temperature process to manufacture such planar optical
waveguides.

It is a further object of the present invention to propose a
technique to manufacture such waveguides in a low-cost, mass-
15 fabrication technology.

It is still a further object of the present invention to
provide optical waveguides that show low mechanical stress and
a significantly reduced stress-related birefringance.

20

Still another object of the present invention is the provision
of silicon-oxide based optical waveguides that could be
integrated into conventional CMOS technology.

25 These and other objects and advantages are achieved by the
material disclosed in claim 1 and the method claimed in claim
3.

Preferred embodiments of the invention are described in the
30 dependent claims.

To achieve the above mentioned objects, a new material for the
manufacture of planar optical waveguides is proposed as set
forth in independent claim 1.

35

Brief Description of the Drawings

The invention will be described in more detail hereinafter in connection with the drawings, in which

5

Fig. 1 is an infrared spectrum showing the NH-absorption band of conventional SiON:H material as compared to the SiON:D material according to the invention;

10 Fig. 2 shows the slab propagation loss of SiON:D as compared to the SiON:H material annealed according to the state of the art;

Fig. 3 depicts the compressive stress as a function of
15 temperature for state of the art material as compared to the material according to the invention; and

Fig. 4 shows a plot of the estimated birefringence
20 dependent on compressive stress.

Detailed Description of the Preferred Embodiment

25 Silicon-oxinitride (SiON) layers can function as planar optical waveguides in the 1550-nm wavelength region. The optically guiding SiON waveguide core layer has a relatively high refractive index of 1.500 and is sandwiched between two silicon-oxide cladding layers with a lower refractive index
30 of 1.450. The SiON layer is deposited by PECVD using silane, nitrous oxide and ammonia as gaseous precursors. Waveguide bends with a radius of curvature as small as 1.5 mm can be realized because of high refractive index difference achievable between core and cladding layers. This allows the

fabrication of compact, relatively complex integrated optical waveguide devices.

Owing to the hydrogenated precursors, the conventional, state of the art SiON layers (in the following called SiON:H) contain a large number of N-H bonds with their intrinsic infrared absorption at a wave number of 3350 cm^{-1} . The first overtone of this frequency is found at a wavelength of 1510 nm and its low-energy tail leads to an unwanted absorption loss in the wavelength region of interest (1545 to 1565 nm). Fig. 1 shows a typical absorption spectrum of a state of the art planar slab waveguide structure with an as-deposited SiON core layer (SiON:H; lower curve). A typical loss for unannealed SiON:H material is 10 dB/cm at 1510 nm and 1.0 - 1.2 dB/cm at 1550 nm (a factor of 10x higher than annealed material). The N-H bonds can be largely removed by annealing the SiON layers in an atmospheric nitrogen flow at a temperature of approximately 1140°C. The peak losses at 1510 nm then decrease to a value of 1.0 dB/cm, and the losses between 1545 and 1565 nm decrease to typical values of $0.15 \pm 0.05\text{ dB/cm}$ what is shown in Fig. 2.

However, this high-temperature annealing process is an expensive manufacturing step which, in addition, slows down the wafer turnaround time. Moreover, stress build-up follows upon cooling down the relaxed layers from high-temperature, due to mismatched thermal expansion. The induced stress effects result in stress-related polarization dependence (birefringence). In addition to that, since the waveguide fabrication is a „high-temperature“ process, only special substrate materials can be used which are able to stand these high temperatures.

The present invention therefore proposes a „low-temperature“ process for the manufacture of planar slab optical waveguides

based on SiON material by using a deuterated SiON material (in the following called SiON:D). „Low temperature“ here means that the foreseen maximum temperature of all process steps is in the range of 550 - 850°C, including densification steps and tuning of mechanical stress. A „densification window“ of 550 - 850°C might also be useful to stabilize the SiON:D properties. By using SiON:D material, the above mentioned anneal cycle at 1400°C (taking 22 hours) is avoided. Thus, the work-flow is simplified and a wider process latitude is given as the use of a wider temperature window is allowed. Moreover, the proposed method offers the possibility to integrate the optical waveguides into a conventional CMOS process for further hybrid integration. In addition to that, low mechanical stress in the oxidic layer stack can be achieved, the estimated lowering of compressive stress in SiON:D material is by a factor 3,5 from about -270 to -80 MPa (cf. Fig. 3). The typical value for SiON:H material is -120 MPa (as-grown) and -270 MPa (after 1145°C anneal). In contrast to that the value for SiON:D material according to the invention is -115 MPa (as grown), no anneal is necessary. The calculated unannealed SiON:D value of -80 MPa shown in Fig. 3 is based on best estimates on the time the invention was made, the currently cited value is based on three SiON:D wafers with a value of -115 +/- 10 MPa. The quoted stress values pertain to planar SiON:D and planar SiON:H layers on SiO₂ (lower cladding) base layers. For a full waveguide device, these SiON:X layers (X = H, D) are covered with a top-cladding SiO₂ layer to form an oxidic tri-layer. This overgrowth of SiON:X has the effect of making the oxidic sandwich mechanically more symmetric and hence lowers the residual stress and thus the stress-related birefringence.

An estimate of this birefringence is shown in Fig. 4, estimating that the SiON:X trilayer waveguide devices of the present invention will have zero-birefringence (or polarization independent) at a compressive stress of -80 to

-100 MPa. It is also noted that an ultimate slight compressive stress (about -50 MPa) is probably advantageous for a multi-layered device in order to remain mechanically intact, because a lower or tensile stress value might easily lead to delamination, peeling off and structural insufficiency. Thus the SiON:D according to the present invention offers far better mechanically tuning opportunities than annealed SiON:H, where the loss-lowering procedure determines the temperature history and hence the residual stress.

10

It has to be noted that the new method also offers the advantages already present when using annealed SiON:H material, namely eliminating N-H loss (cf. Fig. 2; lower curve), thus opening a wider wavelength window for SiON photonic ICs, realization of radius of curvature of as small as 1.5 mm, etc., associated with the high refractive index of SiON.

As compared to the state of the art processes already mentioned before, the method according to the invention does not change the starting materials by replacing hydrogen with deuterium but starts already using deuterated gaseous precursors, namely SiD_4 and/or ND_3 . The work performed proves that the largest contribution to the conventional N-H loss at 1510 nm originates from the N-H precursor. Starting the process using ND_3 as a precursor lowers the loss to the annealed, conventional value of SiON:H. Using both hydrogenated precursors, SiD_4 and ND_3 , lowers the loss >5x over the conventionally annealed SiON:H material. It has to be mentioned that only small deuterated gas-volumes are consumed and thus the process is very cost-effective. The present plasma deposition process consumes per full SiON:D core 4" wafer three liters of ND_3 and 30 liters of 2% SiD_4 (diluted in He), this implies about 330 full 4" SiON:D wafers from a standard gas cylinder.

- The incorporation of nitrogen, „N-doping”, has a far stronger effect on refractive index than B-, P- or Ge-doping, because the N-doping continuously changes the host material, in contrast to light additives as B, P or Ge. The effect of nitrogen on the refractive index is about 10x stronger and thus an adequate optical „bending” into a 1.5 mm radius is obtained at a nitrogen atomic content of $8.0 \pm 1\%$ N at a refractive index of 1.510. The preferred range of nitrogen is about 3 to about 15 atomic %; the 3% lower limit gives some advantage in waveguide radius over conventional Ge:SiO₂ and is easily detectable, the 15% as a high limit will give a radius of about 0.5 mm.
- The preferred composition in relative atomic fractions [%] of the SiON:D material is as follows, with, e.g., the „N atomic fraction” being the amount of N atoms divided by the sum of the sum of Si, O and N atoms.

Element	Fraction
Si	10
O	19
N	0.05 - 0.10
D	0.05 - 0.15
H	< 0.01

- As has been previously mentioned, either one or both precursors for the manufacture of SiON waveguides, namely NH₃ and SiH₄, can be deuterated. Five precursor mixtures have been used in the evaluation of infrared absorption and optical loss. The following table gives the improvement factors as compared to the standard-annealed hydrogenated SiON:H material (M1).

	Mixture	Improvement	Remarks
M1	SiH ₄ /NH ₃ /N ₂ O	--	Reference SiON
M2	SiD ₄ /ND ₃ /N ₂ O	5-7x	All deuterated
M3	SiH ₄ /ND ₃ /N ₂ O	Marginal	SiH ₄ and N ₂ O
M4	SiD ₄ /--/N ₂ O	Marginal	Other Chemistry
M5	SiD ₄ /NH ₃ /N ₂ O	None	Contains NH ₃

„Other chemistry“ in M4 indicates there is not the usual plasma chemistry using SiH/NH/NO (or its D-isotopes), but
 5 rather SiH/NO without NH; thus the chemical reaction or synthesis routes are different.

This indicates that by far the largest contribution of N-H in SiON:H originates from the NH₃ gas in the current SiH₄/NH₃/N₂O
 10 mixture.

Improvement in optical loss at 1510 nm by a factor 5 to 7 is
~~obtained with the set M2 without annealing, compared to the~~
 standard SiON:H hydrogenated results after annealing. Loss
 15 figures in dB/cm are compared in the following table (cf. Also Fig. 2).

Process		Loss @ 1510 nm	Loss @ 1540 nm
Standard	SiON:H	1.0 ± 0.2	0.13 ± 0.02
M2	SiON:D	0.16 ± 0.02	0.07 ± 0.02

20 The method according to the invention comprises the following steps:

- A) Oxidation of silicon wafer to a defined thickness by oxygen diffusion at high temperature;
- 25 B) Deposition on SiON waveguide layer by Plasma-CVD;
- C) Definition of ridge structure via lithography and etching in the SiON core layer;

- D) Overgrowth of core/ridge structure with SiO_2 by Plasma-CVD or by thermal CVD;
- E) Densification of the overgrowth layer to adjust birefringence; and
- 5 F) Dicing of wafer into individual chips and polishing of optical input/output facets of the individual devices.

Fig. 3 shows the compressive stress as a function of temperature. It can be seen that the material according to the
10 invention (SiON:D) has a significantly lower value of stress than the conventionally produced material (SiON:H).

In Fig. 4 there is provided a plot of the estimated dependence of birefringence on the compressive stress in a waveguide.
15 Given a value of about -80 MPa for the material according to the invention, it is clearly perceptible that the resulting birefringence is drastically decreased.

The outstanding advantage of the proposed method is the
20 complete elimination of N-H related absorption in SiON leading to ultra- low loss material with a wide optical bandwidth. The proposed technique is a low-cost, mass-fabrication technology when implemented in PECVD for two reasons: (i) small deuterated gas-volumes are consumed and (ii) expensive
25 manufacturing processing steps like high-temperature annealing are eliminated. Thus, a faster wafer turnaround time is obtained.

The avoidance of the anneal cycle simplifies the process
30 workflow and gives a wider process latitude as it allows the use of a wider temperature window, allowing the design of other cladding/sintering treatments (densification) to even further lower the stress-related effects. The new process latitude is used to deliberately optimize a moderate
35 temperature cycling for stress adjustment and for the first

time offers the possibility to integrate the optical waveguides into a conventional CMOS process for further hybrid integration. Applications could be optical clock distribution, optical receiver or power drivers for thermal tuning.

5

C L A I M S

1. A composition of matter comprising essentially silicon (Si), oxygen (O), and nitrogen (N), and additionally
5 comprising deuterium (D) and hydrogen (H),

characterized in that


the concentration in relative atomic fractions of D is
10 from about 0.03 to about 0.20 and the concentration in
relative atomic fractions of H is below 0.01.
2. The composition of matter of claim 1, wherein the
concentration of D is from about 0.05 to about 0.15.
- 15 3. The composition of matter according to claim 1 or 2,
wherein the concentration of nitrogen is between 1 and 99
atomic-%.
- 20 4. The composition of matter according to claim 3, wherein
the concentration of nitrogen is between 1 and 50
atomic-%, preferably between 3 and 15 atomic-%.
5. Method for fabricating planar optical waveguides based on
25 silicon oxinitride (SiON) material by means of a PECVD
process,

characterized in that

30 deuterated gaseous precursors are used as starting
materials.
6. Method according to claim 5, wherein the maximum
temperature reached during the process steps is in the
35 range of about 550 to about 850°C.


7. Method according to claim 6, wherein the higher value of the temperature range is only reached in case a densification of the obtained SiON material is necessary.
 - 5 8. Method according to claim 5, wherein the deuterated gaseous precursors are SiD_4 and ND_3 .
 9. Method according to claim 8, wherein only one of said
 - 10 10. Method according to claim 8, wherein both of the gaseous precursors are used.
 - 15 11. Use of the material according to any one of claims 1 to 4 as optical waveguide material.
-

1/4



2/4

Fig. 2







Fig. 3

Fig. 4



INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 00/01763

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C03C3/04 C03C3/11 C03B19/14 C01B21/087 C01B21/082
C23C16/30 G02B6/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C C03B C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

INSPEC, EPO-Internal, COMPENDEX, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	HUBNER J ET AL: "Strong Bragg gratings induced with 248 nm light in buried silicon oxynitride waveguides" BRAGG GRATING, PHOTSENSITIVITY, AND POLING IN GLASS FIBERS AND WAVEGUIDES: APPLICATIONS AND FUNDAMENTALS. TECHNICAL DIGEST. POSTCONFERENCE EDITION, PROCEEDINGS OF BRAGG GRATINGS, PHOTSENSITIVITY, AND POLING IN GLASS FIBERS AND WAVEGUIDES: APPLICATI, 26 October 1997 (1997-10-26), pages 346-350, XP000987165 1997, Washington, DC, USA, Opt. Soc. America, USA ISBN: 1-55752-516-1 page 346	1-4,11
Y	---	5-10
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

5 March 2001

Date of mailing of the international search report

12/03/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Bommel, L

INTERNATIONAL SEARCH REPORT

Inte. onal Application No

PCT/IB 00/01763

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 023 093 A (KIZILYALLI ISIK C ET AL) 8 February 2000 (2000-02-08) column 3, line 22 - line 45; claims	5-10
X	ARNOLDBIK W M ET AL: "Dynamic behavior of hydrogen in silicon nitride and oxynitride films made by low-pressure chemical vapor deposition" PHYSICAL REVIEW B (CONDENSED MATTER), 15 AUG. 1993, USA, vol. 48, no. 8, pages 5444-5456, XP000979362 ISSN: 0163-1829 page 5444 -page 5445	1-4
X	HABRAKEN F H P M ET AL: "Hydrogen in low-pressure chemical-vapor-deposited silicon (oxy)nitride films" JOURNAL OF APPLIED PHYSICS, 15 JAN. 1986, USA, vol. 59, no. 2, pages 447-453, XP000979361 ISSN: 0021-8979 page 447	1-4
X	ARNOLDBIK W M ET AL: "Deuterium diffusion into plasma-deposited-silicon-oxynitride films" APPLIED SURFACE SCIENCE, JAN. 1994, NETHERLANDS, vol. 74, no. 1, pages 103-113, XP000987037 ISSN: 0169-4332 page 103 -page 106	1-4
E	US 6 156 653 A (BERG JOHN E ET AL) 5 December 2000 (2000-12-05) the whole document	1-4
A	GERMANN R ET AL: "Silicon-oxynitride layers for optical waveguide applications" SILICON NITRIDE AND SILICON DIOXIDE THIN INSULATING FILMS. PROCEEDINGS OF THE FIFTH INTERNATIONAL SYMPOSIUM (ELECTROCHEMICAL SOCIETY PROCEEDINGS VOL.99-6), PROCEEDINGS OF THE FIFTH INTERNATIONAL SYMPOSIUM ON SILICON NITRIDE AND SILICON DIOXIDE THIN I, pages 169-181, XP000987166 1999, Pennington, NJ, USA, Electrochem. Soc, USA ISBN: 1-56677-228-1 page 169 -page 170	1-11

-/--

INTERNATIONAL SEARCH REPORT

Int. onal Application No

PCT/IB 00/01763

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO 99 44937 A (BLOEHL PETER ;GERMANN ROLAND (CH); MASSAREK ILANA (CH); SALEMINK) 10 September 1999 (1999-09-10) page 4, line 25 -page 9, line 15</p>	1-11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 00/01763

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6023093 A	08-02-2000	JP 10303424 A	13-11-1998
US 6156653 A	05-12-2000	NONE	
WO 9944937 A	10-09-1999	EP 0983208 A	08-03-2000

Form PCT/ISA/210 (patent family annex) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.